

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01J 33/00, C11C 3/12, B01J 31/02	A1	(11) International Publication Number: WO 95/30481 (43) International Publication Date: 16 November 1995 (16.11.95)
(21) International Application Number: PCT/US95/05395 (22) International Filing Date: 2 May 1995 (02.05.95) (30) Priority Data: 94201289.9 9 May 1994 (09.05.94) EP (34) Countries for which the regional or international application was filed: AT et al. (71) Applicant (for BB only): ENGELHARD CORPORATION [US/US]; 101 Wood Avenue, Iselin, NJ 08830 (US). (71) Applicant (for all designated States except BB US): ENGELHARD DE MEERN B.V. [NL/NL]; Strijkviertel 67, NL-3454 ZG De Meern (NL). (72) Inventor; and (75) Inventor/Applicant (for US only): VAN DIJK, Gustaaf, J., M. [NL/NL]; Meeuwiskamp 6, NL-3755 JN Eemnes (NL). (74) Agents: MILLER, Stephen, I. et al.; Engelhard Corporation, 101 Wood Avenue, Iselin, NJ 08830 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CN, CZ, DE, DK, EE, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report.</i>
(54) Title: HYDROGENATION CATALYST PARTICLES (57) Abstract The invention is directed to hydrogenation catalyst particles based on nickel or cobalt and a support, incorporated in a matrix of hardened oil or a derivative thereof, which matrix material is solid at a temperature of 25 °C, said particles having an average weight of at least 120 mg and an average height of at least 2.8 mm.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Larvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Title: Hydrogenation catalyst particles

The present invention relates to catalyst particles based on nickel or cobalt and a support, incorporated in a matrix of hardened oil or a derivative thereof.

Such catalysts are well known, and are employed in particular for the hydrogenation of oils and fats. These triglycerides, often containing polyunsaturated fatty acid chains, are often hydrogenated prior to use, so as to increase stability and/or to adjust the melting behaviour.

Increasing the stability of the polyunsaturated triglycerides is accomplished by hydrogenation of the readily oxidizable polyunsaturated bond. Oxidation of these bonds is undesirable, as this gives rise to a rancid taste.

Adjusting the melting behaviour of the product is particularly important with a view to rendering the product suitable for use in margarines, hard shortening and cocoa butter substitutes.

Another important application of these catalysts is the hydrogenation of fatty nitriles to obtain amines, such as primary, secondary and tertiary amines. Also in the hydrogenation of free fatty acids supported nickel and cobalt catalysts are used.

There are numerous publications dealing with these supported nickel or cobalt catalysts, such as EP-A 92,878, EP-A 167,201, EP-A 168,091, EP-A 168,096, EP-A 340,848, EP-A 384,542, EP-A 398,446, EP-464,956 and EP-A 566,197.

In commercial practice the supported nickel or cobalt catalysts, when intended to be used in powder form, for example in batch processes, are delivered to the customer incorporated in a matrix of hardened oil or, when used for nitrile hydrogenation, in solid fatty nitrile or fatty amine.

Important parameters in developing these catalysts are the improvement of selectivity, of activity and of filterability. Generally the work on these subjects has been concentrated on the modification of either the
5 characteristics of the catalyst itself or of the hydrogenation process parameters.

Especially in the edible oil industry some producers prefer to start the hydrogenation at relatively low temperature, that is at about 120°C, or even lower, thereby
10 using the exotherm to heat the reactor to the desired final temperature. This saves energy input and increases the capacity as the cycle time is shortened. In order to be able to decrease the starting temperature, it is of course important that the catalyst has sufficient activity at this
15 low temperature. It has been found that the conventional catalysts do not give sufficient low temperature activity.

It is an object of the present invention to provide for a catalyst that is suitable for this purpose.

The present invention is based on the surprising fact
20 that the low temperature activity of a catalyst is influenced by the shape and size of the actual product used in the hydrogenation plant, that is the matrix of hardened oil (fat) or derivative thereof, in which the catalyst itself is incorporated.

The present invention is accordingly directed to
25 hydrogenation catalyst particles based on nickel or cobalt and a support, incorporated in a matrix of hardened oil or a derivative thereof, which matrix material is solid at a temperature of 25°C, said particles having an average weight
30 of at least 120 mg and an average height of at least 2.8 mm.

The average weight of the catalyst particles can easily be determined from a representative sample of a production batch of the catalyst particles using appropriate sampling techniques (for example an amount of sample of at least
35 10 g), simply by determining the weight of a known number of particles and dividing the total weight by the number of particles. The average height is determined by averaging the

height of the particles from the same sample. This height is defined as the smallest size of the particle. In case hemispherical particles are used, the height is the distance between the flat underside and the top of the particle. In
5 case more or less spherical particles are used the size is simply the diameter (or smallest diameter) of the particle. In case of flakes the size is the smallest distance between two opposite surfaces of the flake.

Conventional catalyst particles did not possess the
10 presently defined combination of features, as they had either an average weight or an average height below the required value. A number of catalysts are known having an average height of about 2.4 to 2.8 mm, in many cases in combination with an average weight of between 60 and 100 mg.
15 One catalyst had an average weight of about 150 mg, but this catalyst did not have the required height, namely only about 2.6 mm. None of those prior art catalysts possess the very good low temperature properties of the catalysts according to the invention.

20 The particles of the present invention have an average height of at least 2.8 mm, preferably at least 2.9 mm, more in particular at least 3.0 mm. The upper limit is not very critical, as the object of the invention is reached when meeting the lower limit. For practical purposes the upper
25 limit will not be more than 12 mm, as it is rather difficult to prepare and to use particles that have a height above this value.

The average weight of the particles of the present invention is at least 120 mg. According to preferred
30 embodiments the weight is more than 130 mg, more in particular more than 140 mg, as above those limits the optimal results are obtained. Again the upper limit is not very critical, as it is mainly determined by the limits put upon the particles by production and use. Generally the
35 upper limit is about 500 mg, preferably 300 mg.

The particles of the present invention can be prepared in a number of manners, but preferably by preparing a

suspension of the supported nickel or cobalt catalyst powder (elementary catalyst particles), typically having a size in the range of 1 to 100 μm , in a melt of the hardened oil or a derivative thereof, and letting droplets of the said
5 suspension fall on a cooled plate, resulting in solid particles having an essentially hemispherical shape.

Other methods of producing the catalyst particles are i.a. letting droplets of the suspension fall into a cooled fluid, where they solidify to more or less spherical
10 particles (prilling in air or liquid), or flaking the suspension to flakes of a suitable thickness.

When using hemispherical particles the surface to volume ratio is less than 1.75 mm^{-1} , preferably between 0.5 and 1.75 mm^{-1} .

15 The matrix material of the particles can be a hardened oil or derivative thereof. Examples thereof are hardened vegetable, or less preferred animal, oils, as well as the solid derivatives thereof, such as fatty nitriles and fatty (primary, secondary and tertiary) amines.

20 The catalyst content in the particles can range between wide limits. Generally it will not be more than 35 wt.% of nickel or cobalt, based on the weight of the particles. A preferred upper limit is about 30 wt.%, whereas the lower limit will be determined by economical considerations,
25 resulting in a value of at least 5 wt.%, preferably at least 10, more in particular at least 15 wt.%.

The invention is directed generally to those catalysts that are used for the hydrogenation of (animal or vegetable) oils, free fatty acids and/or nitriles. All suitable
30 supported nickel or cobalt catalysts can be used in the particles. The catalysts described in the cited references, the contents of which references is incorporated herein by way of reference, can for example be used in the particles. Other catalysts that can be included in a matrix of hardened
35 oil (fat) or derivative thereof, may also be used.

The actual composition of the elementary catalyst particles is not very critical, although it is preferred to

have a nickel or cobalt content between 5 and 95 wt.%, preferably between 15 and 75 wt.%. The size of the nickel crystallites may vary between 1 and 15 nm, and the nickel surface area can be between 5 and 250 m²/g of nickel.

- 5 As a support the conventional supports can be used such as the oxidic supports. Examples are silica, alumina and silica-alumina. The BET surface area of the elementary catalyst particles may be between 75 and 450 m²/g, determined according to R. Haul and G. Dömbgen
10 (Chem. Ing. Techn.; 35, 586, (1963))

Values outside those ranges can also be used, although they are not preferred.

- The determination of the various parameters can be done using conventional techniques. The nickel crystallite size
15 may be determined from the line broadening in the X-ray diffraction pattern. The nickel surface area may be determined by H₂-chemisorption, using the assumption that one nickel atom occupies 6.5 Å² (Ref.: Yates et al, JACS 86, pp. 2996-3001, 1964).

- 20 The catalyst may be promoted with various promoters. Some of these are disclosed in the cited references. Important promoters include magnesium, copper, iron and sulphur, which may be used in varying amounts, such as between 0.1 and 15 wt.%, calculated on the weight of the
25 nickel or cobalt.

- The material to be hydrogenated using the particles of the invention includes the materials discussed in the introductory part, which include oils, both of animal and vegetable nature, and derivatives thereof, based on C₁₂ to
30 C₂₂ triglycerides, for example the C₁₂ to C₂₂ fatty acids and nitriles.

The invention is elucidated on the basis of the following examples, without being limited thereto.

EXAMPLES 1 and 2

Two lots of catalyst particles were tested for their
5 activity in the hydrogenation of soy bean oil, having a
iodine value of 131.6. One lot had an average weight of 40
mg and an average height of 1.7 mm (Example 1). The second
lot had an average weight of 175 mg and an average height of
3.1 mm (Example 2). Prior to the use thereof all lots of
10 catalyst particles were stored for two weeks at 30°C in air,
in order to eliminate the influence of different storage
conditions.

Using a catalyst concentration of 0.01 wt.% of nickel,
soy bean oil was hydrogenated at 120°C for 60 minutes at a
15 hydrogen pressure of 0.70 bar. The results of the
experiments were that the catalyst of Example 1 resulted in
a decrease of the iodine value of 15.1, whereas the catalyst
of example 2 gave a decrease of 21.2.

This clearly shows that the size of the actual particles
20 has a profound influence on the activity in this experiment.

CLAIMS

1. Hydrogenation catalyst particles based on nickel or cobalt and a support, incorporated in a matrix of hardened oil or a derivative thereof, which matrix material is solid at a temperature of 25°C, said particles having an average weight of at least 120 mg and an average height of
5 at least 2.8 mm.
2. Catalyst particles according to claim 1, wherein the particles have an average weight of at least 130, more in particular at least 140 mg.
- 10 3. Catalyst particles according to claim 1 or 2, wherein the average height of the particles is at least 2.9, preferably at least 3.0 mm.
4. Catalyst particles according to claim 1-3, wherein the catalyst is a supported nickel catalyst.
- 15 5. Catalyst particles according to claim 1-4, wherein the amount of nickel in the particles, calculated on the basis of the combined weight of catalyst and matrix does not exceed 35 wt. %.
6. Catalyst particles according to claim 1-5, wherein
20 the nickel or cobalt content of the catalyst is between 5 and 95 %, based on the combined weight of the support and the nickel or cobalt.
7. Catalyst particles according to claim 1-6, wherein the particles have an essentially hemispherical shape.
- 25 8. Catalyst particles according to claim 7, wherein the surface to volume ratio is less than 1.75 mm^{-1} , preferably between 0.5 and 1.75 mm^{-1} .
9. Use of the catalyst particles according to claim 1-8 in the hydrogenation of animal or vegetable oil.

10. Use of the catalyst particles according to claim 1-8 in the hydrogenation of fatty nitrile to fatty amine.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 95/05395

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B01J33/00 C11C3/12 B01J31/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B01J C11C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP-A-0 186 885 (HEINKEL KOMMANDITGESELLSCHAFT) 9 July 1986 SEE ESPECIALLY COLUMN 3, LINES 19-32, COLUMN 5, LINES 35-54, COLUMN 7, LINES 1-13 AND 40-52 ----	1
A	DE-A-28 50 719 (A. WINSEL) 10 July 1980 ----	
A	FR-A-1 555 015 (W.R. GRACE & CO) 24 January 1969 ----	
A	FR-A-802 536 (RUHRCHEMIE A.G.) 7 September 1936 ----	
A	GB-A-1 042 923 (AIR PRODUCTS AND CHEMICALS, INC.) 21 September 1966 ----	
	-/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

25 July 1995

Date of mailing of the international search report

04.08.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Devisme, F

INTERNATIONAL SEARCH REPORT

ational Application No

PCT/US 95/05395

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP-A-0 464 956 (ENGELHARD DE MEERN B.V.) 8 January 1992 cited in the application -----</p>	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 95/05395

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0186885	09-07-86	DE-A- 3447782 JP-B- 6024637 JP-A- 61161146 US-A- 4808562	10-07-86 06-04-94 21-07-86 28-02-89
DE-A-2850719	10-07-80	NONE	
FR-A-1555015	24-01-69	NONE	
FR-A-802536	07-09-36	NONE	
GB-A-1042923		NONE	
EP-A-0464956	08-01-92	NL-A- 9001536 DE-D- 69101751 DE-T- 69101751 JP-A- 4227064 US-A- 5223470	03-02-92 26-05-94 25-08-94 17-08-92 29-06-93

THIS PAGE BLANK (USPTO)